

EXHIBIT K



SABIC® PP PCGH10

PP homopolymer for Healthcare

Description:

SABIC® PP grades for healthcare applications are produced under controlled conditions resulting in high product quality, consistency and a high level of purity.

SABIC® PP PCGH10 is typically designed for healthcare applications, such as caps and closures, parts for medical devices and medical film. This grade offers a high stiffness with moderate impact strength.

Compliance to regulations:

SABIC®PP PCGH10 complies with the relevant monographs of the European Pharmacopoeia (EP) and the United States Pharmacopoeia (USPVI). The product mentioned herein may not be used for medical healthcare devices or materials intended for temporary or permanent implementation in the human body.

Typical values

Revision 20110221

Properties	Unit (SI)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg at 230 °C and 5 kg	g/10 min g/10 min	10.5 38	ISO 1133
Density	kg/m ³	905	ISO 1183
Mechanical properties			
Tensile test stress at yield stress at break strain at break	MPa MPa %	43 34 600	ISO 527
Flexural test Flexural modulus	MPa	1800	ASTM D 790
Izod impact notched at 23 °C	kJ/m ²	2.0	ISO 180/4A
Charpy impact notched at 23 °C	kJ/m ²	1.5	ISO 179
Hardness Shore D	-	72	ISO 868
Thermal properties			
Heat deflection temperature at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B)	°C °C	54 98	ISO 75/A ISO 75/B
Vicat softening temperature at 10 N (VST/A) at 50 N (VST/B)	°C °C	152 90	ISO 306/A ISO 306/B



SABIC® PP PCGH10

PP homopolymer for Healthcare

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.